



Maad RF Light Premium DB

Density: 60 kg/m³ + 3,5mm (layer)

Thickness: 3 – 100 mm

Width: 1000 mm

Type of material:

Black closed-cell flexible elastomeric foam (FEF) covered with acoustic barrier.

Product range:

Flat sheets or rolls (also in a self-adhesive version) with thicknesses from 3 to 100 mm.

Fields of application:

Thermal and acoustic insulation, refrigeration, air-conditioning and heating & plumbing services in commercial, industrial and domestic applications

Dimensional tolerance:

In accordance with the European Standard EN 14304.

Environmental information:

Flexible and expanded CFC and HCFC-free rubber foam. It does not damage the ozone layer (ODP zero) and does not contribute to the greenhouse effect (GWP zero).

Technical Data

Properties	Result	Test Method
Operating temperature range:	-40 °C + 130 °C	EN 14706/EN 14707
Thermal conductivity λ: At a mean temperature of 0 °C:	≤0.040 W/m·K	EN 12667/EN ISO 8497
At a mean temperature of + 40 °C	≤0.042 W/m·K	
Fire performance: Europen standard	B-s3,d0	EN 13501 -1
UK:	Fire propagation i1≤ 6.0 Surface spread of flame Class 1 Building Regulations Class 0	BS476: Part 6 BS476: Part 7 BS476 Parts 6 and 7

USA, Canada	UL Approved Flame Class V-0 5VA	UL 94 UL 746 A
Switzerland:	Flame Class V.2	
Ozone resistance:	Excellent	ISO 7326
UV resistance:	Good	UNI ISO 4892-2
Antimicrobial behaviour:	Meets test requirements	AATCC test method 30-2004
Corrosion risk:	Meets test requirements	EN 13468

Acoustic Data

Sound insulation factor R'
according to ISO 717-1 29 dB (A)

Loss factor

DIN 53440 to 200 Hz, on 1mm stainless
temperature range (-20°C - +40°C) 0,06 – 0,27

Storage conditions/shelf life:

Store the material in a dry and clean environment
at a temperature between 0 °C and 35 °C and a RH between 50% and 70%. Do not expose the material to heat or direct
sunlight before installing. Tapes and self-adhesive sheets should not be kept in storage for more than one year.

For all adhesive materials it is important that the surface is clean, dry and free of grease, oil and solvents.

All specifications are mean values and are made to the best of one's knowledge, are however not binding and exclude any
requirements of any kind regarding damages or failures to third-party property rights. Tests should be carried out by the
buyer.